



## 2. HEMPEL'S GALVOSIL 15700

SURFACE PREPARATION:	Remove oil and grease, etc. with suitable detergent. Remove salt and other contaminants by (high pressure) fresh water cleaning. Gritblasting to minimum Sa 2½ with a surface profile equivalent to Rugotest No. 3, BN10a, Keane-Tator Comparator, min. 3.0 G/S, or ISO Comparator rough MEDIUM (G). Consult separate Application Instructions, and - as relevant - the corresponding PAINTING SPECIFICATION for cargo tanks.
APPLICATION CONDITIONS:	The surface must be completely clean and dry with a temperature above the dew point to avoid condensation. At temperatures ranging from -10°C/15°F to 40°C/105°F. Curing needs minimum 65% relative humidity. Consult separate APPLICATION INSTRUCTIONS.
SUBSEQUENT COAT:	None.
REMARKS:	<b>Note:</b> If used as anticorrosive protection under insulation of high temperature equipment it is very important that NO moisture can penetrate during shut-down periods. This to avoid risk of "wet corrosion" when the temperature rises. Wet service temperature, non-saline water: Maximum 60°C/140°F. Wet service temperature, other liquids: Consult the corresponding CARGO PROTECTION GUIDE.
Film thicknesses:	If topcoated with a heavy- duty system, 50 micron/2 mils dry film thickness (75 micron/3 mils wet) is recommended. Consult separate Application Instruction before recoating. For long-term protection without topcoat, 75 micron/3 mils dry film thickness (100-125 micron/4-5 mils wet) is generally recommended. In tanks 100 micron/4 mils dry film thickness (150 micron/6 mils wet) is recommended but may be applied in 125 micron/5 mils dry film thickness (200 micron/8 mils wet).  Minimum interval for recoating with: 20°C/68°F, 65-75% RH  HEMPADUR (system/high-build)                      3 days, full curing (see APPLICATION INSTRUCTIONS)      HEMPADUR (25 micron/1 mil)                      24 hours
Recoating:	Recoating intervals are strongly dependent on both temperature and humidity. Deviations from the standard conditions may shorten or prolong the recoating intervals. Consult separate APPLICATION INSTRUCTIONS. The recoating interval of 24 hours for 25 micron/1 mil HEMPADUR is only valid in case the subsequent coat is applied more than 1 week after (20°C/68°F), 75% RH, humid weather. Otherwise, the minimum recoating interval is the same as for system/high-build.
Curing:	Before cargo tanks are taken into use, the coating must be completely through-cured. It is recommended to carry out low pressure hosing of the tanks with (fresh) water 2-3 times. Let the tanks remain wet between the washings. Reference is made to APPLICATION INSTRUCTIONS.
Note:	<b>HEMPEL'S GALVOSIL 1570 is for professional use only.</b>
SAFETY:	Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult HEMPEL Material Safety Data Sheets and follow all local or national safety regulations. Harmful or fatal if swallowed; immediately seek medical assistance if swallowed. Avoid inhalation of possible solvent vapours or paint mist, as well as paint contact with skin and eyes. Apply only in well ventilated areas and ensure that adequate forced ventilation exists when applying paint in confined spaces or when the air is stagnant. Always take precautions against the risks of fire and explosions.

This Product Data Sheet supersedes those previously issued. For definition and scope, see explanatory notes to applicable Product Data Sheets. Data, specifications, directions and recommendations given in this data sheet represent only test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the Products herein must be determined exclusively by the Buyer and/or User. The Products are supplied and all technical assistance is given subject to HEMPEL's GENERAL CONDITIONS OF SALES, DELIVERY AND SERVICE, unless otherwise expressly agreed in writing. The Manufacturer and Seller disclaim, and Buyer and/or User waive all claims involving, any liability, including but not limited to negligence, except as expressed in said GENERAL CONDITIONS for all results, injury or direct or consequential losses or damages arising from the use of the Products as recommended above, on the overleaf or otherwise.

Product data are subject to change without notice and become void five years from the date of issue.

Issued by HEMPEL'S MARINE PAINTS A/S.

\*This is a corporate trademark of the Hempel Group.

August 1997 - 1570019840CO025