

# HEMPEL'S ANTI-SLINT\* 67500

**Description:** HEMPEL'S ANTI-SLINT 6750 is flame dried silica sand of which the average particle size is approximately 0.5 millimetre.

**Recommended use:** To obtain anti-skid properties on decks and other areas where a skid-proof surface is required.

**Availability:** Subject to confirmation.

## PHYSICAL CONSTANTS:

Colour: Greyish  
Specific gravity: 2.7 (approx.) kg/litre  
Particle shape: Grit

**REMARKS:** Being heavy and rather coarse HEMPEL'S ANTI-SLINT 6750 should not be stirred into the paint before its application. For such purpose use HEMPEL'S ANTI-SLIP BEADS 6742 (consult the product data sheet).  
HEMPEL'S ANTI-SLINT 6750 should be sprinkled evenly on the surface immediately upon application of the penultimate coat of the paint system while the paint is still wet. Consumption approximately 2.5 kg/5.5 lbs of HEMPEL'S ANTI-SLINT 6750 to 25 sq.m/ 270 sq.feet.  
When the paint is dry, sweep up surplus grit and apply the final coat.  
HEMPEL'S ANTI-SLINT 6750 should be kept dry and clean.  
Do not mix contaminated sweepings with new supplies.

**Note:** **HEMPEL'S ANTI-SLINT 6750 is for professional use only.**

This Product Data Sheet supersedes those previously issued. For definition and scope, see explanatory notes to applicable Product Data Sheets.

Data, specifications, directions and recommendations given in this data sheet represent only test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the Products herein must be determined exclusively by the Buyer and/or User. The Products are supplied and all technical assistance is given subject to HEMPEL's GENERAL CONDITIONS OF SALES, DELIVERY AND SERVICE, unless otherwise expressly agreed in writing. The Manufacturer and Seller disclaim, and Buyer and/or User waive all claims involving, any liability, including but not limited to negligence, except as expressed in said GENERAL CONDITIONS for all results, injury or direct or consequential losses or damages arising from the use of the Products as recommended above, on the overleaf or otherwise. Product data are subject to change without notice and become void five years from the date of issue.

Issued by HEMPEL'S MARINE PAINTS A/S.

\*This is a corporate trademark of the Hempel Group.

September 1996